

Type N PVC Pipe Cement Clear

Specially formulated resin-based adhesive

Product Description

Plumbtec Pro Type N PVC Pipe Cement Clear is a specially formulated resin-based adhesive for bonding PVC-U pipe, fittings and sheet. It is fast setting and generally recommended for PVC-U Pipes with a diameter of 150mm or less. Some fittings 150mm and above may require a Gap Filling Solvent Cement.

Areas of Application

Plumbtec Pro Type N PVC Pipe Cement Clear is suitable for Non-Pressure applications in residential, commercial and industrial work such as:

- Sewerage
- Drainage,
- Storm Water
- Electrical
- Cable Conduit

Features & Benefits

- Manufactured to the highest Australian Standards and Quality Assurance so the Plumbtec Pro Type N PVC Pipe Cement Clear comes with a 10-year manufacturer's warranty.
- Conforms to the stringent performance requirements of AS/NZS 3879 so you can have confidence it will do the job.
- AS/NZS 4020 approved, which means it is suitable for use in contact with drinking water.
- Watermark and ISO 9001:2008 accredited so quality assurance is assured.
- All Packaging is Dangerous Goods approved

Features & Benefits cont.

- Tightly engineered cap to minimise the risk of leaks.
- Range of sizes to suit any job.
- All containers are supplied with a bristle brush applicator cap to ensure easy application.
- Proven product performance over several decades in millions of applications around Australia and overseas.

AS/NZS 3879 SHEAR STRESS TEST
REQUIREMENTS FOR TYPE N

PRODUCT DATA	
Appearance	Clear Viscous Liquid
Specific Gravity @ 20°C	0.88 – 0.90
Viscosity @ 20 C, cPs	500 - 700
Contents	100% Hydrocarbon Liquids.

DRYING TIME	JOINT STRENGTH TO EXCEED	
20 Minutes	0.1 MPa	100 kPa or 14.5 psi
1 Day	1 MPa	1,000 kPa or 145 psi
60 Days	4 MPa	4,000 kPa or 580 psi

VOC Levels

The Green Building Council of Australia has advised that "Pipe cements are not relevant to the VOC credit as they have little influence on indoor air quality. Plumbing pipes are usually installed some time prior to building occupation and any residual of solvent will be negligible by the time the building is sealed and occupied. In addition plumbing pipes are not a major component of an individual fit-out or building, plumbing cements are minor in quantity in the indoor fit-out when compared to adhesives used in countless other indoor applications." (GBCA Technical Clarification Statement PVC Pipe Cements IEQ-13, Clarification No. 43, October 2009). Refer to the GBCA website for more information www.gbca.org.au

Application

PVC Pipe Cement Jointing is a trade skill and should only be executed by appropriately qualified trades' people. Refer to AS/NZS 2032 for complete PVC Pipe Cement jointing instructions.

Preparing the Joint

1. Ensure pipe is cut square and remove burrs.
2. To ensure correct assembly of joint, mark pipe at a distance equal to full socket depth.
3. Test joint for dry fit.
4. Clean pipe and inside of socket using a clean cloth freshly moistened with Plumbtec Priming Fluid. This is essential to ensure a satisfactory bond.

Making the Joint

1. Shake or stir thoroughly before using.
2. Apply Plumbtec Pro Solvent Cement in full even coats to both surfaces firstly to the inside of socket, then to external surface of pipe end.

Making the Joint cont.

3. Immediately assemble, pushing the pipe home to the full depth of the socket.
4. Hold bonded joint in position for at least 30 seconds.
5. Do not disturb for 5 minutes.
6. Allow 24 hours curing before testing.

The open time of Plumbtec Pro Solvent Cement, which is the time from the beginning of adhesive application until the joining of the parts, is dependent on the temperature and on the thickness of the adhesive layer. With an adhesive layer of 1 mm and at the temperature given below, the parts should be joined within the following times:

PRODUCT DATA	
20 °C	4 min
25 °C	3 min
30 °C	2 min
40 °C	1 min
> 40 °C	< 1 min

For the first 5 minutes after cementing, avoid moving the pipes. At temperatures of less than 10°C, this should be extended to 15 minutes. If in the ground, cemented jointed pipes may be covered after approximately 10-12 hours. Before using the pipes in normal operation, thoroughly flush them through with water to remove any solvent vapour.

Where pipes are not required for immediate service, it is advisable to flush through thoroughly and possibly allow to stand filled with water.

Packaging & Shelf Life

Shelf Life is 2 years if unopened and stored in a cool, dry, well-ventilated place out of direct sunlight.

Handy Tips

- Keep the lid tightly on Plumbtec Pro Priming Fluid and Plumbtec Pro Solvent Cements when not in use. Evaporation of the solvents will affect the quality and performance of the Plumbtec Pro Solvent Cement.
- Plumbtec Pro Solvent Cement should have a "syrup-like" consistency. Do not use it if it is lumpy or "jelly-like" consistency.
- No additive of any kind (including Priming Fluid) should be mixed with Plumbtec Pro Type N PVC Pipe Cement Clear.
- PVC Pipe Cements take no longer to set in colder temperatures. Do not try to artificially speed up the drying process of Plumbtec Pro Type N PVC Pipe Cement Clear by using hair-dryers or the like. This could affect the integrity of the joint.
- Avoid spilling the Plumbtec Pro Type N PVC Pipe Cement Clear. In the event of spillage, soak up as quickly as possible with a clean dry cloth.

Limitations

- Plumbtec Pro Type N Cement is to be used for Non-Pressure Applications only. For Pressure Applications use Plumbtec Pro Type P Cement.

Limitations cont.

- Temperatures above 30°C and/or windy conditions can result in premature drying of Plumbtec Pro Solvent Cement and prevent a satisfactory bond. In such circumstances either apply a second coat or use a Slow Setting Pipe Cement.
- For PVC pipes with a diameter exceeding 150mm we recommend using a Slow Setting Pipe Cement or Large Diameter Pipe Cement.
- Not suitable for bonding polyethylene or plasticised PVC articles.

Safety Directions

Irritant. Avoid breathing vapour. Avoid contact with skin and eyes. Highly Flammable and Keep away from Flames.

NOT TO BE TAKEN. REFER TO MATERIAL SAFETY DATA SHEET FOR ADDITIONAL INFORMATION.

If poisoning occurs contact a doctor or Poisons Information Centre. Phone: Australia 131 126 NZ: 0800 764 766 or a doctor immediately. If swallowed do not induce vomiting. Give a glass of water.

Disclaimer

The information and any recommendations relating to the application and end-use of all Plumbtec products are provided in good faith based on Plumbtec's knowledge and experience of the products. In applications, the differences in materials, and variances of substrates and actual site conditions can vary such that no warranty in respect of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be taken as inferred either from this information, or from any written recommendations, or from any other advice offered by Plumbtec. The proprietary rights of third parties must be observed. All orders are accepted subject to our sale terms and conditions. All users should always refer to the most recent and up to date issue of the Technical Data Sheet for the product concerned, which is available on request. It is recommended that products should always be properly stored, handled and applied under tested and recommended conditions. PLEASE CONSULT OUR TECHNICAL DEPARTMENT FOR FURTHER INFORMATION.



Manufactured for Plumbtec Pro by:
RLA Polymers Pty Ltd
ACN 004 709 915 215
Colchester Road Kilsyth, Victoria 3137, Australia
(PO Box 147)
Tel: 1800 242 931
sales@rlapolymers.com.au