

Wet Area Silicone

Neutral curing, premium quality silicone sealant for wet areas.

Product Description

Plumbtec Wet Area Silicone is an anti-fungal, non-diluted, high performance, UV resistant, neutral-cure, silicone sealant. It is specially formulated to seal joints or seams in ceramics, plaster, metal and timber (natural or painted) in kitchens, bathrooms, laundries, toilets or wherever fungal growth might occur.

Areas of Application

- Perimeter sealing of baths, basins, shower basins, spas and sinks
- Ceramic and other tiles (note: natural stone must be pre-tested to ensure the product does not stain).
- Window frames.
- Exhaust fans.
- Metal fixtures including shower frames.

Features & Benefits

- Manufactured to the highest Australian Standards and Quality Assurance so the Plumbtec Wet Area Silicone comes with a 10 year manufacturer's warranty.
- 100% Silicone so it does not shrink when curing and customers do not pay for solvents or fillers.
- Excellent adhesion properties so it adheres to most surfaces, included painted surfaces, and the job only needs to be done once

Features & Benefits cont.

- Neutral (Non-Acetic) Cure is non-corrosive and so does not react with metals and other surfaces.
- Permanently flexible so it resists cracking, shrinking and vibration.
- Suitable for interior and exterior applications so the product is very versatile.
- Unaffected by extreme temperature (hot or cold) so suited to any environment.
- Waterproof so it provides a flexible watertight seal.
- Low VOC which means low vapour, low odour and a safer work environment for the plumber or trades person.
- UV resistant so it is not affected significantly by sunlight, making it more durable.

Application

Surface preparation

Surfaces to be sealed must be clean and dry. Ensure there is no foreign matter including grease, wax, flaking paint etc. Complete all painting before applying Silicone

Making the Joint

- Use masking tape on each side of the joint to protect surfaces and to ensure a neat job.
- Cut nozzle at 45°C angle to desired thickness.
- Cut nub on cartridge. Insert cartridge into a caulking gun.
- Hold gun at 45° angle with nozzle in contact with both sides of joint.
- Apply by pushing Plumbtec Wet Area Silicone ahead of nozzle.
- Smooth off before skin forms
- Remove excess Plumbtec Wet Area Silicone immediately with a cloth dampened with mineral spirit or turpentine.
- Remove any masking tape immediately sealant tooling is complete.
- Plumbtec Wet Area Silicone skins in 5 minutes and is touch dry in 30 minutes.

Clean Up

Cured Plumbtec Wet Area Silicone can be removed by trimming with a sharp blade

Packaging & Shelf Life

Shelf Life is 12 months if stored in a cool (below 25°C), dry, well-ventilated place and out of direct sunlight.

Handy Tips

- Do not apply to wet surfaces. Ensure surfaces are clean and dry.
- All applications should be pre-tested to ensure the finished results with Plumbtec Wet Area Silicone meet the expectations of the user.
- Adhesion of Plumbtec Wet Area Silicone to substrates should be pre-tested to ensure there is adequate adhesion.
- Pre-test Plumbtec Wet Area Silicone on substrates for any potential staining. This is especially relevant for natural stone like marble.
- Also refer to SAFETY DIRECTIONS below.
- Not to be used for structural glazing.
- Not paintable.
- Not to be used on extruded type polycarbonates or polyacrylates as cracking may occur
- Not recommended for use in trafficable applications or continually submersed conditions
- Not recommended for below water line applications.
- Not recommended for applications in which it will be in constant contact with chlorinated water.

Safety Information

On contact, uncured sealant causes irritation. Gloves and protective goggles must be worn during application and use. Avoid contact with skin, eyes and avoid breathing in vapour. Wear protective gloves when mixing or using. If poisoning occurs contact a doctor or Poisons Information Centre. Phone: Australia 131 126 NZ: 0800 764 766 or a doctor immediately. If swallowed, do not induce vomiting. Give a glass of water. If skin contact occurs, remove contaminated clothing and wash skin thoroughly for a minimum of 15 minutes and see a doctor. For more detailed information refer to the Safety Data Sheet.

PRODUCT DATA	
Appearance	White or Clear Paste
Specific Gravity @ 20°C	1.03 g/mL
Tooling/Skin Time @20°C	5 - 12 minutes
Cure Time	24 hours @ 2 mm depth or 5 days for full cure @ 10mm depth
Application Range	10°C to + 35°C
Performance Range	-60°C to +175°C
Hardness Shore A	28
Tensile Strength	2.0 MPa
Sag, Slump	Nil
Joint Movement	+/- 25% Min

Disclaimer

The information and any recommendations relating to the application and end-use of all Plumbtec products are provided in good faith based on Plumbtec's knowledge and experience of the products. In applications, the differences in materials, and variances of substrates and actual site conditions can vary such that no warranty in respect of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be taken as inferred either from this information, or from any written recommendations, or from any other advice offered by Plumbtec. The proprietary rights of third parties must be observed. All orders are accepted subject to our sale terms and conditions. All users should always refer to the most recent and up to date issue of the Technical Data Sheet for the product concerned, which is available on request. It is recommended that products should always be properly stored, handled and applied under tested and recommended conditions. PLEASE CONSULT OUR TECHNICAL DEPARTMENT FOR FURTHER INFORMATION.



Manufactured for Plumbtec Pro by:
 RLA Polymers Pty Ltd
 ACN 004 709 915 215
 Colchester Road Kilsyth, Victoria 3137, Australia
 (PO Box 147)
 Tel: 1800 242 931
sales@rlapolymers.com.au